

Continuous synthesis of atomically dispersed Rh supported on MgAl₂O₄ in hydrogen production from liquid hydrocarbon

Qiangqiang Xue¹, Binhang Yan¹, Yujun Wang¹, and Guangsheng Luo¹

¹Tsinghua University

March 31, 2022

Abstract

Single-atom catalysts with optimal atom utilization and outstanding activity have penetrated the frontier of heterogeneous catalysis. However, the large-scale synthesis of this class of catalysts is still a bottleneck for their industrialization. Herein, we suggest a two-stage micro-dispersion approach to synthesize mesoporous MgAl₂O₄-supported atomically dispersed Rh, which is more competitive than the batch method for boosting the uniform dispersion of Rh. By increasing the Rh loading, SACs (< 0.05wt%), SACs + NPCs (0.05–0.17 wt%), and NPCs (0.17–1.10 wt%) were obtained and then characterized by the HADDF-STEM technique. For n-octane steam reforming, the TOF of the SAC (0.01 wt%) was approximately 30 times that of the NPC (1.10 wt%), while the Rh amount of SAC was only 3% that of the NPC for the same fuel conversion. Under a high-temperature (750 °C) steam atmosphere for 15 h, the hydrogen formation rate only declined from 25.1 to 23.8 mol/mol-C₈H₁₈.

Hosted file

Manuscript.docx available at <https://authorea.com/users/467062/articles/563144-continuous-synthesis-of-atomically-dispersed-rh-supported-on-mgal2o4-in-hydrogen-production-from-liquid-hydrocarbon>