

# An insight into cyclic oxidation behaviour of $\text{ZrB}_2$ -20 vol.% $\text{MoSi}_2$ based ultra-high temperature ceramic matrix composite between $1100^\circ\text{C}$ and $1300^\circ\text{C}$

Mainak Saha<sup>1</sup>

<sup>1</sup>Affiliation not available

December 5, 2022

*Mainak Saha<sup>1,2</sup>*

<sup>1</sup>Department of Metallurgical and Materials Engineering, National Institute of Technology, Durgapur-713209, India

<sup>2</sup>Department of Metallurgical and Materials Engineering, Indian Institute of Technology Madras, Chennai-600036, India

**Abstract** - While descending through different layers of atmosphere with tremendously high velocities, hypersonic re-entry nosecones fabricated using ultra-high temperature ceramic matrix composites (UHTCMCs) are subjected to repeated thermal shocks. This necessitates extensive investigations on the cyclic oxidation behaviour of UHTCMCs at temperatures ranging from  $1100^\circ\text{C}$  to  $1300^\circ\text{C}$  (service temperature of the nosecones). To this end, the present work is aimed at investigating the cyclic oxidation behaviour of  $\text{ZrB}_2$  -20 vol.% $\text{MoSi}_2$  (ZM20) UHTCMC (a very widely investigated ZM CMC) by carrying out cycles for 6h, at 1 cycle/h and estimating oxidation kinetic law. This has been followed by extensive characterisation using X-Ray Diffraction (XRD) to indicate the phases formed during oxidation and Scanning electron microscopy-energy dispersive spectroscopy (SEM-EDS), in order to determine the chemical composition of the oxides formed between  $1100^\circ\text{C}$  and  $1300^\circ\text{C}$ .

**Keywords**- Borides; ceramic composites; cyclic oxidation; kinetics; oxide layer

Among UHTCs,  $\text{ZrB}_2$ -based ceramics have been reported to be potential candidates for the manufacture of reusable Thermal Protection Systems (TPS) in Hypersonic re-entry nosecones, due to very high thermal conductivity and relatively low density [1,2]. However, the low fracture toughness and poor thermal shock resistance of these ceramics pose major obstacles to their use in extreme environment [3]. Moreover, the poor oxidation resistance of  $\text{ZrB}_2$  at temperatures above  $1200^\circ\text{C}$ , due to formation of  $\text{B}_2\text{O}_3$ , and a non-protective porous scale of  $\text{ZrO}_2$  [4], poses restrictions to its use at elevated temperatures, especially above  $1200^\circ\text{C}$ . Thus, it becomes extremely important to find materials, which may highly enhance the oxidation resistance of  $\text{ZrB}_2$  [5-8]. A significant amount of work has already been done in that direction [8-12]. Besides, a significant amount of research has been done on reinforcing diborides like  $\text{ZrB}_2$ ,  $\text{HfB}_2$  and  $\text{TiB}_2$  with  $\text{SiC}$ ,  $\text{MoSi}_2$ , or  $\text{ZrSi}_2$  for enhanced oxidation resistance beyond  $800^\circ\text{C}$  [3- 23]. However, a limited amount of study has been made on cyclic oxidation of ZM20 at temperatures exceeding  $1100^\circ\text{C}$ , which is not at all unlikely, in the context of Hypersonic nosecones, during a high velocity descent through different layers of atmosphere. Thus, the scope of the present study is to investigate the cyclic oxidation behaviour of ZM20 between  $1100$  and  $1300^\circ\text{C}$ .

The important conclusions drawn from the results and discussions of this study have been elucidated. Cyclic oxidation behaviour of  $\text{ZrB}_2$ -20 vol.%  $\text{MoSi}_2$  composite have been studied at  $1100^\circ\text{C}$ ,  $1200^\circ\text{C}$ ,  $1250^\circ\text{C}$  and

1300 °C for 6hrs. Monitoring weight change and examining oxide scales draw following conclusions:

(i) Weight gain for both the composites increased with increasing temperature and time. (ii) Weight gain occurred due to formation of ZrO<sub>2</sub> and SiO<sub>2</sub>, at elevated temperatures. (iii) The main oxidation products were ZrO<sub>2</sub>, MoO<sub>3</sub> and SiO<sub>2</sub>. (iv) At 1200 °C and above, the presence of SiC particles markedly improves the resistance to oxidation of the composite due to the formation of borosilicate glass.

(v) Due to formation of oxide layer on the surface, the hardness of the samples i.e. its mechanical properties decreased from center to surface.

(vi) The cyclic oxidation of the samples follow linear oxidation kinetics from 1100 to 1250 °C while at 1300 °C it follows parabolic oxidation kinetics due to the protective action of SiO<sub>2</sub> above 1250 °C.

The results of the present study and their analyses lead to the following directions for future work: (i) The oxidation kinetics of the samples beyond 1300 °C can be studied. (ii) Residual strain calculations can be carried out. (iii) Mathematical modelling study of the oxidation kinetics can be carried out. (iv) TEM study of the samples can be carried out for more precarious measurements. (v) Carrying out diffusion studies on oxide layer. **Acknowledgement** The authors are grateful to the Department of Metallurgical and Materials Engineering, NIT Durgapur and Central Research Facility(CRF), IIT Kharagpur, for their support to carry out the work and hereby declare no conflict of interest.

## References

- [1] Monteverde F, Bellosi A, Luigi S. Processing and properties of ultra-high temperature ceramics for space applications. *Mater Sci Eng* 2008;485:415–21. [2] Levine SR, Opila EJ, Halbig MC, Kiser JD, Singh M, Salem JA. Evaluation of ultra-high temperature ceramics for aeropropulsion use. *J Eur Ceram Soc* 2002;22:2757–67. [3] Pastor M. Metallic borides: preparation of solid bodies, sintering methods and properties of solid bodies. In: Matkovich VI, editor. *Boron and refractory borides*. New York: Springer; 1977. p. 457–93. [4] Meeson GA, Gorbunow AF. Activated sintering of zirconium boride. *Inorg Mater* 1968;4:267–70. [5] Kinoshita M, Kose S, Hamanos Y. Hot-pressing of zirconium diboride–molybdenum disilicide mixtures. *Yogyo-Kyokai-Shi* 1970;78:32–41. [6] Guo SQ, Yang JM, Tanaka H, Kagawa Y. Effect of thermal exposure on strength of ZrB<sub>2</sub>-based composites with nano-sized SiC particles. *Compos Sci Technol* 2008;68:3033–40. [7] Niihara K, Nakahira A. In: Vincentini P, editor. *Advanced structural inorganic composites*.
- [8] Mallik M, Roy S, Ray KK, Mitra R. Effect of SiC content, additives and process parameters on densification and structure–property relations of pressureless sintered ZrB<sub>2</sub>–SiC composites. *Ceram Int* 2013;39:2915–32. [9] Zhang SC, Hilmas GE, Fahrenholtz WG. Mechanical properties of sintered ZrB<sub>2</sub>–SiC ceramics. *J Eur Ceram Soc* 2011;31:893–901. [10] Liu Q, Han W, Zhang X, Wang S, Han J. Microstructure and mechanical properties of ZrB<sub>2</sub>–SiC composites. *Mater Lett* 2009;63:1323–5. [11] Ikegami M, Guo S, Kagawa Y. Densification behavior and microstructure of spark plasma sintered ZrB<sub>2</sub>-based composites with SiC particles. *Ceram Int* 2012;38:769–74. [12] Cao M, Wang S, Han W. Influence of nanosized SiC particle on the fracture toughness of ZrB<sub>2</sub>-based nanocomposite ceramic. *Mater Sci Eng A* 2010;527:2925–8. [13] Patel M, Singh V, Reddy JJ, Bhanu Prasad VV, Jayaram V. Densification mechanisms during hot pressing of ZrB<sub>2</sub>–20 vol% SiC composite. *Scr Mater* 2013;69:370–3. [14] Quo SQ. Densification of ZrB<sub>2</sub>-based composites and their mechanical and physical properties: a review. *J Eur Ceram Soc* 2009;29:995–1011. [15] Zhu M, Wang Y. Pressureless sintering ZrB<sub>2</sub>–SiC ceramics at low temperatures. *Mater Lett* 2009;63:2035–7. [16] Zhang X, Liu Q, Han W, Han J. Microstructure and mechanical properties of ZrB<sub>2</sub>–SiC nanocomposite ceramic. *Scr Mater* 2009;61(7):690–2. [17] Tripp WC, Davis HH, Graham HC. Effect of an SiC addition on the oxidation of ZrB<sub>2</sub>. *Am Ceram Soc Bull* 1973;52(8): 612–6. [18] Rezaie A, Fahrenholtz WG, Hilmas GE. Oxidation of zirconium diboride-silicon carbide at 1500 °C at a low partial pressure of oxygen. *J Am Ceram Soc* 2006;89(10): 3240–5. [19] Mashhadi M, Khaksari H, Safi S. Pressureless sintering behavior and mechanical properties of ZrB<sub>2</sub>–SiC composites: effect of SiC content and particle size. *J Mater Res Technol* 2015;4(4):416–22. [20] Sciti D, Guicciardi S, Bellosi A. Properties of a pressureless-sintered ZrB<sub>2</sub>–MoSi<sub>2</sub> ceramic composite. *J Am Ceram Soc* 2006; 89(7):2320–2.

- [21] Saha M, New frontiers in characterising ZrB<sub>2</sub>- MoSi<sub>2</sub> ultra-high temperature ceramics, arXiv: 2202.11162.
- [22] Saha M, Cyclic Oxidation behaviour of ZrB<sub>2</sub>-20 vol.% MoSi<sub>2</sub> based ultra-high temperature ceramic matrix composite between 1100 C and 1300 C, engrxiv.org.
- [23] Saha M, On the structure-property correlation in pressureless sintered porous ZrB<sub>2</sub>-20 vol.% MoSi<sub>2</sub> ultra-high temperature ceramic matrix composites, submitted for publication.